

CIGWELD

AN ESAB BRAND



SPATTER RELEASE AGENT

DO NOT COVER THIS INFORMATION & WARNING.

DIRECTIONS FOR USE: Apply CIGWELD Spatter-Safe holding the nozzle approximately 300mm from the surface to be protected. Spray in a fine mist to cover the surface (care should be taken to avoid build-up of Spatter-Safe in the joint to be welded. The same technique should be used to protect the interior and exterior of nozzles, the end and outer surface of contact tips and all surfaces subject to weld spatter, even those remote from the arc. Diffusers and the base of the nozzle support should also be treated.

IMPORTANT:

Spatter-Safe should be applied sparingly in a fine mist.
Excess application may be detrimental to weld quality.

NOTE:

When used in conjunction with urethane paints and other high technology finishes, take care to ensure compatibility. To remove Spatter-Safe from surfaces use concentrated detergent and rinse well with water. Normal degreasing practices should be observed.

For further information contact:

CIGWELD Customer Care,

71 Gower Street, Preston VICTORIA 3072

Telephone: 1300 654 674 Email: enquiries@cigweld.com.au